

Technical Data Sheet

technicoll® 9508 Cyanoacrylate, odourless



Field of application

technicoll® 9508 is a multipurpose, low-viscous and odourless cyanoacrylate for bonding small surface areas of plastics, rubber (e.g. EPDM), metal, ceramics, leather, paper, etc..

Handling data and product data

Base	alkoxy ester
Viscosity (+20 °C)	40 - 80 mPas
Density	approx. 1.0 g/cm ³
Temperature range	approx. -30 °C to +70 °C (depending on substrate and mechanical load)
Colour	colourless, transparent
Way of application	one-sided
Processing temperature	+15 °C to +25 °C
Dilution	not possible
Cleaning agent / material	technicoll® 8363 technicoll® 9901 (metal cleaning spray) technicoll® 9902 (plastics cleaning spray)
Cleaning	Cured adhesive can be removed with technicoll® 9602.
Maximum time of storage	At least 1 year when stored in sealed original packaging in cool and dry places.
Preferred storage temperature	+2 °C to +10 °C. Adhesive should be warmed up to room temperature before use.
Behaviour at low temperature	Densification at low temperature. Once adjusted to processing temperature: fully employable.

Favoured substrates

- rubber
- metal
- ceramics, porcelain
- PE, PP, POM, TPE (incl. pretreatment with primer technicoll® 9605-1)
- EPDM (cellular rubber)
- plastics (unplasticised)

Not suitable for: PTFE (Teflon®), silicone, PVC-p (faux leather)

Due to the large variety of possible materials and differences in adhesion behaviour hazard tests are mandatory before introducing the adhesive into the actual production process.

Surface preparation

Joint surfaces must be dry and clean, especially free of oil, grease or release agents.

Curing time

Amongst others, it depends highly on the material. Initial strength is being achieved by:

Metal (steel) / metal (steel)	approx. 20 – 50 seconds
Elastomer (EPDM) / elastomer (EPDM)	approx. 1 – 3 seconds
ABS / ABS	approx. 1 – 3 seconds
Wood (beech tree) / wood (beech tree)	approx. 40 – 60 seconds

Lap shear strength

Steel / steel	10 – 25 N/mm ²
NBR / NBR	material failure

Technical status: 22.12.2015

Deviating information of earlier versions is invalid.

page 2/2

Special notice:

All information given on this data sheet is based on our knowledge and experience at the time of printing. The information is not binding. We advise to determine the suitability of our products with respect to their intended use and method of application. Therefore, a warranty claim cannot be granted.