

Technical Data Sheet

technicoll® 9607 Adhesion promoter for PVC



Field of application

technicoll® 9607 is an adhesion promoter for PVC, PUR, polyesters and polyethers. When cross linking agent technicoll® 9962 is added to technicoll® 9607, the pot life is approx. 3 hours.

Handling data and product data

Base	mixture of solvents
Viscosity (+20 °C)	approx. 500 mPas
Cross linking agent	technicoll® 9962
Pot life	approx. 3 hours
Mixing ratio (weight)	100:5
Density	approx. 0.8 g/cm ³
Processing temperature	+18 °C to +25 °C
Maximum time of storage	At least 6 months when stored in sealed original packaging in cool and dry places.
Behaviour at low temperature	Not susceptible to frost.
Preferred storage temperature	+10 °C to +25 °C

Surface preparation

Bonding surfaces must be dry and clean, especially free of oil, grease or solvents. In many cases, roughening the surfaces to be bonded improves bond strength.

Technical status: 22.12.2015

Deviating information of earlier versions is invalid.

page 1/1

Special notice:

All information given on this data sheet is based on our knowledge and experience at the time of printing. The information is not binding. We advise to determine the suitability of our products with respect to their intended use and method of application. Therefore, a warranty claim cannot be granted.